

CHEMONIT 18 HT

PRODUCT DESCRIPTION

CHEMONIT 18 HT is a high graphite-filled and electrostatic dissipating hard rubber lining based on Natural rubber (NR).

FIELDS OF APPLICATION

CHEMONIT 18 HT is used mainly for the workshop rubber lining of steel components servicing under chemical loads. The field of applications are mainly chemical plants, chlorine and steel industry, mineral processing plants and environmental protection plants. Some typical examples of applications are the rubber linings of storage tanks and reaction vessels, columns, centrifuges, crystallization reactors and tube bundle heat exchangers (shell & tube heat exchangers) operating at higher temperatures. Due to its good electrical conductivity, **CHEMONIT 18 HT** can be used in processes where the static electricity must be avoided.

FEATURES

- Very good chemical resistance against mineral acids, bases and aqueous phases with organic ingredients
- Excellent diffusion resistance
- Strong resistance against temperature excursions
- High thermal stability (max. +120°C)
- Application onto steel components
- Workshop rubber lining

CHEMICAL RESISTANCE

Information on the chemical resistance properties is available upon request.

SUBSTRATE

Substrates are components made of non-ferrous metals, cast iron, non-alloyed or austenitic steel. Components to be rubber lined shall be designed and manufactured in accordance with EN 14879-1.

SURFACE PRE-TREATMENT

All surfaces to be rubber lined must be dry and free of contaminants. All contaminants, including non-visible detectable contaminants, must be removed in accordance with DIN TR 55684 or EN ISO 8502.

Non-alloyed steel surfaces shall be abrasive blasted to "Near White Metal" in accordance with EN ISO 12944-4. A surface preparation degree of SA 2½ (SSPC-SP 10; NACE No. 2) as specified in EN ISO 8501-1 and a "medium (G)" roughness degree as specified in EN ISO 8503-2 must be achieved. A minimum surface profile of $R_z \geq 60 \mu\text{m}$ is required.

To prevent flash rust, the primer must be applied immediately after the blasting and cleaning of the substrate or the component must be air conditioned to a relative humidity of $\leq 40\%$.

ENVIRONMENTAL CONDITIONS

Throughout the rubber lining process, the temperatures of the substrate and rubber lining materials shall be maintained within the range specified by TIP TOP. All surfaces shall be maintained at a temperature at least 3K above the dew point in order to prevent condensation.

ADHESIVE SYSTEM

CHEMONIT 18 HT is bonded onto steel components by using **ADHESIVE SH-3A SOLUTION**.

APPLICATION METHOD AND CONSUMPTION

During the application of the product, the application instruction must always be observed.

Coat	Product	Application Method	Coverage [g/m ²]
1. Coat steel	ADHESIVE SH-3A SOLUTION	Brush	ca. 200
2. Coat steel	ADHESIVE SH-3A SOLUTION	Brush	ca. 200
1. Coat rubber	ADHESIVE PARA SOLUTION or ADHESIVE SH-3A SOLUTION	Brush	ca. 150 (PARA) ca. 200 (SH-3A)

For steam vulcanization or for special applications (e.g. rubber lining on stainless steel) the two-component primer system **PRIMER HG 1** & **PRIMER HG 2** is additionally applied prior to the 1st Coat steel.

Coat	Product	Application Method	Coverage [g/m ²]
1. Primer steel	PRIMER HG 1	Roll / Spray	ca. 150
2. Primer steel	PRIMER HG 2	Brush	ca. 150

CLEANING

Clean all equipment with **SOLVENT CF-CE** immediately after use.

VULCANISATION

The details given in the application instruction must be observed during vulcanisation.

Place	Vulcanisation Method
Workshop	Vulcanisation in an autoclave under pressure by means hot air or steam.

SPARK TEST

Due to its electrostatic properties (electrical conductive), the rubber lining can not be tested on pores or cracks by means of high voltage test. The rubber lining is tested on pores and cracks by 100% visual inspection with optimal illumination.

SAFETY MEASURES

The material safety data sheets of the individual components, the safety instructions on the packing (label) as well as the legal requirements for handling hazardous materials must be observed.

CHEMONIT 18 HT

PACKING UNITS

The products are supplied in the following standard package sizes:

Product	Size	Article No.
ADHESIVE PARA SOLUTION	6 kg	538 1504
ADHESIVE PARA SOLUTION	21 kg	538 1460
ADHESIVE SH-3A SOLUTION	4 kg	538 1410
ADHESIVE SH-3A SOLUTION	8 kg	538 1511
ADHESIVE SH-3A SOLUTION	21 kg	538 1430
PRIMER HG 1	4.5 kg	525 3050
PRIMER HG 1	9 kg	525 2956
PRIMER HG 2	4.5 kg	525 3060
PRIMER HG 2	9 kg	525 2987
SOLVENT CF-CE	10 l	595 9163

PACKAGING OF RUBBER SHEETS

The rubber sheets are wrapped with PE-separating sheets on cardboard cores, and packed freely suspend in stable, stackable card boxes, to avoid pressure points.

CHEMONIT 18 HT is manufactured by extrusion in the following standard sizes:

Size (Tolerances according EN 14879-4)	Article No.
2 mm x 1100 mm x 10000 mm	529 4300
3 mm x 1100 mm x 10000 mm	529 4310
4 mm x 1100 mm x 10000 mm	529 4320

Size (Tolerances according EN 14879-4)	Article No.
5 mm x 1100 mm x 10000 mm	529 4330
6 mm x 1100 mm x 10000 mm	529 4340

STORAGE

The products must be stored in a cool and dry place, away from direct sunlight. The rubber sheets must be stored free of pressure, best in the original packaging. The rubber sheets may not receive any pressure points. At the specified storage temperatures a shelf life of the products is given of at least for the following periods:

Product	Temperature	Shelf Life
ADHESIVE PARA SOLUTION	≤ +20°C	12 Months
ADHESIVE SH-3A SOLUTION	5 - 20°C	12 Months
CHEMONIT 18 HT	≤ +25°C	3 Months
CHEMONIT 18 HT	≤ +5°C	12 Months
PRIMER HG 1	5 - 20°C	12 Months
PRIMER HG 2	5 - 20°C	12 Months
SOLVENT CF-CE	5 - 25°C	60 Months

If the storage time is exceeded, the materials must be tested before use. Higher storage and transport temperatures will reduce the shelf life. The containers must be kept tightly closed. Liquid products must be stored frost-proof. In addition, the DIN 7716 must be observed.

Technical Data	Standard	Unit	Value
Polymer	ISO 1629 (ASTM D1418)	-	NR
Density	EN ISO 1183-1 (ASTM D792)	g/cm ³	1.42 ± 0.02
Contact Resistance	EN 62631-3-1	Ω · cm	≤ 10 ⁵
Modulus of Elasticity	EN ISO 527 (ASTM D638)	N/mm ²	≥ 900*
Hardness Shore D	ISO 48-4 (ASTM D2240)	-	75 ± 5**
Max. Surface Pressure	-	N/mm ²	10
Adhesion Strength Steel	EN ISO 4624 (ASTM D429; Method E)	N/mm ²	> 6
Elongation at Break	DIN EN ISO 527 (ASTM D638)	%	≥ 2***
Tensile Strength	DIN EN ISO 527 (ASTM D638)	N/mm ²	≥ 25***
Temperature Range	-	°C	-20 up to +120

* Press vulcanisation ** Autoclave vulcanisation *** 4 mm rubber

Note: The indicated temperatures are dependent on the present load and may vary

Information given in the fact sheet above corresponds to the current knowledge available to us regarding our products at the time of its drafting and is intended as a guideline for informational purposes. However, because of the multiple possibilities regarding possible applications, processing and on site conditions, any information given in the fact sheet above is not legally binding, in particular, without being limited to, such information shall not be interpreted as a warranty of merchantability or of fitness for a particular purpose. Customer therefore is advised to conduct its own testing or make an inquiry with our technical department before ordering. We reserve the right to change the product at any time, in particular, without being limited to, minor changes because of advancements in technology. If by way of exception, the information given in the fact sheet above is incorporated by reference into any contract concluded with us under German Law, such information, shall only be interpreted as determining the specific requirements of the contractual products as set out in § 434 BGB (German Civil Code) and shall not be interpreted as constituting a guarantee of condition.

TIP TOP Oberflächenschutz Elbe GmbH | Heuweg 4 | 06886 Wittenberg / Germany
Phone: +49 (0) 3491 635 50 | E-Mail: info@tip-top-elbe.de | Internet: www.tip-top-elbe.com

TIP TOP Oberflächenschutz Elbe GmbH	CHEMONIT 18 HT	Revision 1.06 - 12.03.2021
Replaces all previous editions	PRODUCT INFORMATION	Page: 2/2