

## COROFLAKE 34 M

### PRODUCT DESCRIPTION

**COROFLAKE 34 M** is a combination of a fibreglass mat reinforced laminate lining with a glass flake filled topcoat, both based on a high chemical and thermal resistant Bisphenol-A vinyl ester resin. Due to the excellent mechanical properties, **COROFLAKE 34 M** can cover cracks up to 0.2 mm according to DIBt (German Institute for Construction Technology) guidelines.

### COATING LAYERS CONSUMPTION

The laminate lining consists of the two-component **COROFLAKE N PRIMER**, the three-component **LINING 65** basecoat, the two-component **LINING 65** reinforced layer with one 300 g/m<sup>2</sup> fibreglass mat as well as one 26 g/m<sup>2</sup> C-glass surface veil and at least one coat of the two component **COROFLAKE 34** topcoat. Depending on the present stress, multiple topcoats can be applied. The total applied DFT can be up to approx. 2.0 - 3.0 mm. If a high-voltage testing of the laminate lining on concrete is required, **COROFLAKE N PRIMER AS** must be used as primer instead.

### FIELDS OF APPLICATION

Due to its good crack bridging properties, **COROFLAKE 34 M** is ideal for use of concrete structures such as floors, vessels and pits. It is particularly suitable in flue gas desulphurisation plants according to the sea water process. Due to the excellent chemical resistance **COROFLAKE 34 M** can be also used in many other areas, such as bio gas plants or concrete silos.

### FEATURES

- Good chemical resistance
- Universal application
- Crack-bridging properties
- Outstanding adhesion to concrete
- Can be exposed to process conditions shortly after application

### CHEMICAL RESISTANCE

Information on the chemical resistance properties is available upon request.

### SUBSTRATE

Substrates are components made of concrete, screed or plaster. Components to be coated shall be designed and manufactured in accordance with EN 14879-1. In addition, DIN 1045 must also be observed.

### SURFACE PRE-TREATMENT

Appropriate action shall be taken to prepare the concrete surfaces; dry and free of dust and free of contaminants such as oil or grease. The concrete shall have minimum tensile strength of 1.5 N/mm<sup>2</sup> and minimum compressive strength of 25 N/mm<sup>2</sup>. The residual moisture content must not exceed 4%.

### ENVIRONMENTAL CONDITIONS

Throughout the coating process, the temperatures of the substrate and coating materials shall be maintained within the range specified by TIP TOP. All surfaces shall be maintained

at a temperature at least 3K above the dew point in order to prevent condensation.

### APPLICATION

During the application of the product, the application instruction must always be observed.

Trowel applies the basecoat onto the primed substrate at approx. 1.0 - 1.5 mm. Upon placement of the basecoat, the 300 g/m<sup>2</sup> fibreglass mat is pressed onto the surface and saturated by roller with resin mixture.

Afterwards a 26 g/m<sup>2</sup> C-glass surface veil is pressed onto the surface and saturated by roller with resin mixture. Finally one coat of **COROFLAKE 34** is applied in DFT of 400 - 600 µm per coat as final topcoat. The **COROFLAKE 34** topcoat is applied using an airless air spray system or by rolling or brushing.

In case **COROFLAKE 34** is applied by brushing or rolling, additional coats may be required to achieve the required total DFT. Grinded surfaces must generally be cleaned with **SOLVENT F12**.

**Note:** During application, the lined surface should be shaded from direct or indirect sunlight whenever possible.

### MIXING RATIO

The primer and coating components are supplied in pre-measured units so that weighing or measuring of the components is kept to a minimum. After the unit has been mixed it shall be used within the specified pot life.

Primer (non-conductive)	Parts by Weight	Parts by Volume
<b>COROFLAKE N PRIMER</b>	100	100
<b>HARDENER No. 1 CLEAR</b>	2	2

Primer (conductive)	Parts by Weight	Parts by Volume
<b>COROFLAKE N PRIMER AS</b>	100	100
<b>COROFLAKE ACCELERATOR No. 1</b>	1 - 2	1.1 - 2.1
<b>HARDENER No. 1 CLEAR</b>	2	2

Basecoat	Parts by Weight	Parts by Volume
<b>LINING 65 RESIN</b>	100	100
<b>HARDENER No. 1 CLEAR</b>	2	2
<b>FILLER F1</b>	200	189

Laminate Layer	Parts by Weight	Parts by Volume
<b>LINING 65 RESIN</b>	100	100
<b>HARDENER No. 1 CLEAR</b>	2	2

Topcoat	Parts by Weight	Parts by Volume
<b>COROFLAKE 34</b>	100	100
<b>HARDENER No. 1 CLEAR / RED</b>	2	2.3

## COROFLAKE 34 M

### CONSUMPTION

Layer	Product	Coverage [g/m <sup>2</sup> ]
Primer	<b>COROFLAKE N PRIMER</b> or <b>COROFLAKE N PRIMER AS</b>	ca. 300
Basecoat	<b>LINING 65 RESIN</b>	ca. 1000
	<b>FILLER F1</b>	ca. 2000
Laminate Layer	<b>LINING 65 RESIN</b>	ca. 660
	1 x Fibreglass mat 300 g/m <sup>2</sup>	ca. 330
	1 x C-glass surface veil 26 g/m <sup>2</sup>	ca. 30
Topcoat	<b>COROFLAKE 34</b>	ca. 800 - 1000*

\* Per layer

### POT LIFE / WORKING TIME [min]

Product	15°C	20°C	30°C
<b>COROFLAKE N PRIMER</b>	ca. 60	ca. 40	ca. 20
<b>COROFLAKE N PRIMER AS</b>	ca. 60	ca. 35	ca. 10
<b>LINING 65</b>	ca. 60	ca. 45	ca. 25
<b>COROFLAKE 34</b>	ca. 90	ca. 60	ca. 30

### RECOAT TIME (20°C)

Product	Min. [h]	Max. [Days]
<b>COROFLAKE N PRIMER</b>	ca. 8	ca. 14
<b>COROFLAKE N PRIMER AS</b>	ca. 4	ca. 14
<b>LINING 65</b>	ca. 4	ca. 7
<b>COROFLAKE 34</b>	ca. 4	ca. 3

### CLEANING

Clean all equipment with **SOLVENT T-200** immediately after use.

### SAFETY MEASURES

The material safety data sheets of the individual components, the safety instructions on the packing (label) as well as the legal requirements for handling hazardous materials must be observed.

### PACKING UNITS

The products are supplied in the following standard package sizes:

Product	Size	Article No.
<b>COROFLAKE 34</b>	5 kg	590 1317
<b>COROFLAKE 34</b>	20 kg	590 1300
<b>COROFLAKE ACCELERATOR No. 1</b>	0.4 kg	590 2985
<b>COROFLAKE N PRIMER</b>	5 kg	590 0480
<b>COROFLAKE N PRIMER</b>	20 kg	590 0040
<b>COROFLAKE N PRIMER AS</b>	5 kg	590 2983
<b>COROFLAKE N PRIMER AS</b>	20 kg	590 2990
C-glass surface veil - 26 g/m <sup>2</sup>	250 m <sup>2</sup>	590 9800
E-Glass mat - 300 g/m <sup>2</sup>	20 m <sup>2</sup>	590 0222
E-Glass mat - 300 g/m <sup>2</sup>	20 m <sup>2</sup>	590 0239
E-Glass mat - 300 g/m <sup>2</sup>	50 m <sup>2</sup>	590 0246
<b>FILLER F1</b>	25 kg	591 0140

Product	Size	Article No.
<b>HARDENER No. 1 CLEAR</b>	0.1 kg	590 0181
<b>HARDENER No. 1 CLEAR</b>	0.4 kg	590 0019
<b>HARDENER No. 1 RED</b>	0.1 kg	590 0356
<b>HARDENER No. 1 RED</b>	0.4 kg	590 0112
<b>LINING 65 RESIN</b>	5 kg	590 0435
<b>LINING 65 RESIN</b>	20 kg	590 0411
<b>SOLVENT F12</b>	4 kg	590 0095
<b>SOLVENT T-200</b>	4 kg	590 0610
<b>SOLVENT T-200</b>	8 kg	590 0611

### STORAGE

The products must be stored in a cool and dry place, away from direct sunlight. At the specified storage temperatures a shelf life of the products is given of at least for the following periods:

Product	Temperature	Shelf Life
<b>COROFLAKE 34</b>	5 - 20°C	6 Months
<b>COROFLAKE ACCELERATOR No. 1</b>	5 - 20°C	6 Months
<b>COROFLAKE N PRIMER</b>	≤ 10°C	9 Months
	≤ 20°C	6 Months
<b>COROFLAKE N PRIMER AS</b>	5 - 20°C	6 Months
<b>FILLER F1</b>	-	24 Months
<b>HARDENER No. 1 CLEAR</b>	5 - 20°C	12 Months
<b>HARDENER No. 1 RED</b>	5 - 20°C	12 Months
<b>LINING 65 RESIN</b>	5 - 20°C	6 Months
<b>SOLVENT F12</b>	5 - 20°C	12 Months
<b>SOLVENT T-200</b>	5 - 25°C	60 Months

If the storage time is exceeded, the materials must be tested before use. Higher storage and transport temperatures will reduce the shelf life. The containers must be kept tightly closed. Liquid products must be stored frost-proof. In addition, the DIN 7716 must be observed.



// ONE BRAND // ONE SOURCE // ONE SYSTEM

## COROFLAKE 34 M

Technical Data	Standard	Unit	Value
Abrasion	ASTM D4060	mg	92
Hardness Barcol	EN 59 (ASTM D2583)	-	≥ 30
Min. Adhesion Strength Concrete	EN ISO 4624 (ASTM D7234)	N/mm <sup>2</sup>	1.5*
Test Voltage (earliest after 24 hours)	EN 14879-3	kV / 100µm DFT	0.5
Viscosity	EN ISO 2555 (ASTM D2196)	mPa·s	2750 ± 250
Linear Coefficient of Thermal Expansion	ISO 11359-2 (ASTM C531)	1/K	27-30 x 10 <sup>-6</sup>
Max. Operating Temperature Liquids	-	°C	+75

\* Depending on the concrete strength

**Note:** The indicated temperatures are dependent on the present load and may vary

Information given in the fact sheet above corresponds to the current knowledge available to us regarding our products at the time of its drafting and is intended as a guideline for informational purposes. However, because of the multiple possibilities regarding possible applications, processing and on site conditions, any information given in the fact sheet above is not legally binding, in particular, without being limited to, such information shall not be interpreted as a warranty of merchantability or of fitness for a particular purpose. Customer therefore is advised to conduct its own testing or make an inquiry with our technical department before ordering. We reserve the right to change the product at any time, in particular, without being limited to, minor changes because of advancements in technology. If by way of exception, the information given in the fact sheet above is incorporated by reference into any contract concluded with us under German Law, such information, shall only be interpreted as determining the specific requirements of the contractual products as set out in § 434 BGB (German Civil Code) and shall not be interpreted as constituting a guarantee of condition.

**TIP TOP Oberflächenschutz Elbe GmbH | Heuweg 4 | 06886 Wittenberg / Germany**  
**Phone: +49 (0) 3491 635 50 | E-Mail: [info@tiptop-elbe.de](mailto:info@tiptop-elbe.de) | Internet: [www.tiptop-elbe.com](http://www.tiptop-elbe.com)**

TIP TOP Oberflächenschutz Elbe GmbH	COROFLAKE 34 M	Revision 1.03 - 11.03.2021
Replaces all previous editions	PRODUCT INFORMATION	Page: 3/3